





Specifications

DESCRIPTION	NORM	DATA
Composition fibreuse / Pile Fibre		100% Polyamide (Teint masse/Solution dyed)
Jauge / Gauge		1/10 loop pile
Densité / Tuft Density	ISO 1763	143 500 Stitches/m ²
Poids de fil / Total pile mass	ISO 8543	510 g/m ²
Masse de velours utile / Mass of pile above the substrate	ISO 8543	300 g/m ²
Epaisseur velours utile / Thickness of pile above the substrate	ISO 1766	3.0 mm
Densité du velours de surface / Surface pile density	ISO 8543	0,100 g/cm ³
Masse totale / Total Weight	ISO 8543	3740 g/m ²
Epaisseur totale / Total Thickness	ISO 1765	6.3 mm
Premier dossier / Primary Backing		Non tissé / Non woven primary backing
Envers / Backing		Matières recyclées renforcées par un voile de verre Vinyl backing reinforced with glass fiber (100 % recycled PVC)
Dimensions / Tile Size		50x50cm
Dalles par boîte / Tiles per Box		20 = 5m ²
Sens de pose / Installation		

Technical performances



Classification EN 1307 - 33 / Commercial Heavy









Luxury Class - LC1



Classement UPEC NF 262 - U₃P₃E₁C₀ (certificat n° 349T-008.1)

Feu / Fire rating EN 13501-1 : BflS1



 Heated Floor ISO 10456 0,09 m ² K/W	 Impact noise reduction EN ISO 10143-3 ΔL _(w) 25 dB	RHO - LRV	
		4 colors	%
 Electrostatic prop. ISO 6356 ≤ 2,0kV ISO 10965 RT ≈ 10 ¹⁰ Ω	 Sound absorption ISO 11654 α _w = 0,15 (H)	925	6,4%
		936	10,7%
 Dimensional Stability EN 986 ≤ 0,10%	 Colour Fastness EN 105 - B02 7/8	937	9,8%
		997	6,0%
 N° 0679-CPR-0196 07 EN 14041 : 2004	 Castor Chair EN 985 Passed R _{≥2,4}		

Environmental issues



Les informations ci-dessus peuvent subir des modifications au profit d'une future amélioration / The above information is subject to modifications for the benefit of further improvement.

Mise à jour/Updated on 15/12/2017